

LGMT 2

SKF general purpose industrial and automotive bearing grease

LGMT 2 is mineral oil based lithium soap thickened grease with excellent thermal stability within its operating temperature range. This premium quality, general purposes grease is suitable for a wide range of industrial and automotive applications.



- Excellent oxidation stability
- Good mechanical stability
- Excellent water resistance and rust inhibiting properties

Typical applications:

- Agricultural equipment
- Automotive wheel bearings
- Conveyors
- Small electric motors
- Industrial fans

Bearing operating conditions

Temperature	Medium
Speed	Medium
Load	Low to Medium
Vertical shaft	○
Fast outer ring rotation	—
Oscillating movements	—
Severe vibrations	+
Shock load or frequent start-up	—
Low noise	—
Low friction	○
Rust inhibiting properties	+
+ = Recommended ○ = Suitable — = Not suitable	

Available pack sizes LGMT 2

	35 g tube	200 g tube
420 ml cartridge	1 kg can	5 kg can
18 kg can	50 kg drum	180 kg drum

Technical data

Designations	LGMT 2	
DIN 51825 code	K2K-30	
NLGI consistency class	2	
Soap type	Lithium	
Colour	Red brown	
Base oil type	Mineral	
Operating temperature range, °C (°F)	-30 to 120 (-22 to 250)	
Dropping point DIN ISO 2176, °C (°F)	180 min. (356 min.)	
Base oil viscosity:		
40 °C, mm ² /s	110	
100 °C, mm ² /s	11	
Penetration DIN ISO 2137:		
60 strokes, 10 ⁻¹ mm	265 - 295	
100 000 strokes, 10 ⁻¹ mm	+50 max. (325 max.)	
Mechanical stability:		
Roll stability, 50 hrs at 80 °C, 10 ⁻¹ mm	+ 50 max.	
SKF V2F test	'M'	
Corrosion protection: SKF Emcor:		
- standard ISO 11007	0 - 0	
- water washout test	0 - 0	
- salt water test (100% seawater)	0 - 1*	
Water resistance		
DIN 51 807/1, 3 hrs at 90 °C		1 max.
Oil separation		
DIN 51 817, 7 days at 40 °C, static, %		1 - 6
Lubrication ability		
SKF R2F, running test B at 120 °C		Pass
Copper corrosion		
DIN 51 811, 110 °C		2 max. (130 °C / 266 °F)
Rolling bearing grease life		
SKF R0F test L50 life at 10 000 rpm, hrs		-
EP performance		
Wear scar DIN 51350/5, 1 400 N, mm		-
4-ball test, welding load DIN 51350/4		-
Fretting corrosion		
ASTM D4170 (mg)		-
Designation		LGMT 2/(pack size)
* Typical value		



SKF Maintenance Products

© SKF 2007/01
® SKF is a registered trademark of the SKF Group

The contents of this publication are the copyright of the publisher and may not be reproduced (even extracts) unless permission is granted. Every care has been taken to ensure the accuracy of the information contained in this publication but no liability can be accepted for any loss or damage whether direct, indirect or consequential arising out of use of the information contained herein.